

U.S.S.N. 10/614,456

-2-

GKNG 1165 PUS

In The Claims:

1. (currently amended) A method of producing a roll boot for a constant velocity universal joint from an injection-moldable elastomer, comprising the following steps:

injection-molding a basic member {21} having a cylindrical portion {22} and ~~an~~ a widened portion {23};

turning the basic member {21} completely inside out; and

thereafter, folding the widened portion {23} outwardly so that it partially lies outwards of the cylindrical portion {22}, forming a roll wall {23'} of a finished roll boot.

2. (currently amended) A method of producing a roll boot for a constant velocity universal joint from an injection-moldable elastomer, comprising the following steps:

injection-molding a basic member {31} having a cylindrical portion {32} and two widened portions {33, 43} which adjoin said cylindrical portion {32} at both ends;

turning the basic member {31} completely inside out; and

thereafter, folding the widened portions {33, 43} outwardly, so that they partially lie outwards of the cylindrical portion {32}, forming roll walls {33', 43'} of a finished roll boot.

3. (currently amended) A method according to claim 1, wherein the widened portion {23} is injection-molded to have an approximately conical shape.

4. (currently amended) A method according to claim 2, wherein the widened portions {33, 43} are injection-molded to have an approximately conical shape.

5. (currently amended) A method according to claim 1, wherein the widened portion {23} is injection-molded to comprise a wall thickness which decreases from the cylindrical portion {22} to its free end.

U.S.S.N. 10/614,456

-3-

GKNG 1165 PUS

6. (currently amended) A method according to claim 2, wherein the widened portions ~~(33, 43)~~ are injection-molded to comprise a wall thickness which decreases from the cylindrical portion ~~(32)~~ to their respective free ends.

7. (currently amended) A method according to claim 1, wherein the cylindrical portion ~~(22)~~ is injection-molded to comprise, at its free end, an inner annular groove ~~(24)~~ for receiving a clamping band.

8. (currently amended) A method according to claim 3, wherein the cylindrical portion ~~(22)~~ is injection-molded to comprise, at its free end, an inner annular groove ~~(24)~~ for receiving a clamping band.

9. (currently amended) A method according to claim 5, wherein the cylindrical portion ~~(22)~~ is injection-molded to comprise, at its free end, an inner annular groove ~~(24)~~ for receiving a clamping band.

10. (currently amended) A method according to claim 1, wherein the widened portion ~~(23)~~ is injection-molded to comprise an inner annular bead ~~(25)~~ at its free end.

11. (currently amended) A method according to claim 3, wherein the widened portion ~~(23)~~ is injection-molded to comprise an inner annular bead ~~(25)~~ at its free end.

12. (currently amended) A method according to claim 5, wherein the widened portion ~~(23)~~ is injection-molded to comprise an inner annular bead ~~(25)~~ at its free end.

13. (currently amended) A method according to claim 7, wherein the widened portion ~~(23)~~ is injection-molded to comprise an inner annular bead ~~(25)~~ at its free end.

U.S.S.N. 10/614,456

-4-

GKNG 1165 PUS

14. (currently amended) A method according to claim 2, wherein the widened portions ~~(33, 43)~~ are injection-molded to comprise inner annular beads ~~(34, 35)~~ at their respective free ends.

15. (currently amended) A method according to claim 4, wherein the widened portions ~~(33, 43)~~ are injection-molded to comprise inner annular beads ~~(34, 35)~~ at their respective free ends.

16. (currently amended) A method according to claim 6, wherein the widened portions ~~(33, 43)~~ are injection-molded to comprise inner annular beads ~~(34, 35)~~ at their respective free ends.

17. (currently amended) A method of producing a roll boot for a constant velocity universal joint from an injection-moldable elastomer, comprising the steps of:

injection-molding a basic member ~~(21)~~ having a cylindrical portion ~~(22)~~ and a widened portion ~~(23)~~, the cylindrical portion ~~(22)~~ including, at its free end, an inner annular groove ~~(24)~~ for receiving a clamping band, the widened portion ~~(23)~~ comprising a conical shape, an inner annular bead ~~(25)~~ at its free end, and a decreasing wall thickness from the cylindrical portion ~~(22)~~ to its free end;

turning the basic member completely inside out such that the annular groove ~~(24)~~ and annular bead ~~(25)~~ are outwardly facing; and

thereafter, folding the widened portion ~~(23)~~ outwardly so that it partially lies outwards of the cylindrical portion ~~(22)~~, forming a roll wall ~~(23')~~ of a finished roll boot.

18. (currently amended) A method of producing a roll boot for a constant velocity universal joint from an injection-moldable elastomer, comprising the steps of:

injection-molding a basic member ~~(31)~~ having a cylindrical portion ~~(32)~~ and two widened end portions ~~(33, 43)~~ adjoining the cylindrical portion, each widened portion ~~(33, 43)~~ comprising a conical shape, an inner annular bead ~~(34, 35)~~ at its free end, and a decreasing wall thickness from the cylindrical portion ~~(32)~~ to its free end;

U.S.S.N. 10/614,456

-5-

GKNG 1165 PUS

turning the basic member ~~(31)~~ completely inside out such that the annular beads ~~(34, 35)~~ are outwardly facing; and

thereafter, folding the widened portions ~~(33, 43)~~ outwardly so that they partially lie outwards of the cylindrical portion ~~(32)~~, forming roll walls ~~(33', 43')~~ of a finished roll boot.

19. (original) A roll boot for a constant velocity joint made according to the method of claim 1.

20. (original) A constant velocity joint comprising a roll boot made according to the method of claim 1.